



Hysol® EA 9891RP

Epoxy Paste Adhesive

Henkel Corporation
Aerospace Group
2850 Willow Pass Road
P.O. Box 312
Bay Point, CA 94565 USA
925.458.8000
Fax: 925.458.8030
www.aerospace.henkel.com

Description

Hysol EA 9891RP is a two-component room temperature curing, abrasion resistant repair paste adhesive suitable for repairing SynSpand® 9890 abradable seal.

Features

Two-Component System
Color Change on Mixing
Abrasion Resistant
Room Temperature Curing

Uncured Adhesive Properties

	Part A	Part B	Mixed
Color	Black	Cream	Dark Gray
Density (Lbs/Cu Ft)	44 ± 3	33 ± 3	39 ± 5
Shelf Life @ <85°F/29°C	1 year	1 year	

Handling

Mixing – This product requires mixing two components together just prior to application to the parts to be bonded. Long term storage may induce partial separation of the resins and fillers. Therefore, prior to use, bulk Part A and Part B should be inspected for separation. If separation is evident, mix each part thoroughly prior to mixing the Part A and Part B. Complete mixing is necessary.

	Part A	Part B
Mix Ratio		
By Weight	100	40

Note: Volume measurement is not recommended for structural applications unless special precautions are taken to assure proper ratios.

Pot Life (400g mass) 20 minutes @ 77°F/25°C
Method – ASTM D2471 in water bath.

Application

Mixing – Premix Part A prior to dispensing. Combine Part A and Part B in the correct ratio and mix thoroughly. THIS IS IMPORTANT! Heat buildup during or after mixing is normal. Do not mix quantities greater than 1.5 pounds/680 grams as dangerous heat buildup can occur causing uncontrolled decomposition of the mixed adhesive. WARNING! EXOTHERMIC – TOXIC FUMES CAN OCCUR, RESULTING IN PERSONAL INJURY. The adhesive should be used immediately to prevent a potentially dangerous heat buildup and subsequent uncontrolled decomposition of the mixed adhesive.

Applying – The area to be repaired should be clean, dry and properly prepared. Thin film set time for a 0.125 inch thick film adhesive will occur in 3 hours at 77°F/25°C, after which the support tooling or pressure used during cure may be removed.

Curing – This adhesive is sandable after curing 3 hours at 77°F/25°C. Full cure is attained after 24 hours at 77°F/25°C. A general guideline for determining when the material is sandable is to wait until the paste has a Shore D Hardness measurement of 60 or above. A heating blanket may be used to maintain 77°F/25°C temperatures, however, care must be taken to avoid a potential exotherm. The user needs to simulate repair conditions in order to develop the optimum heat and time cure profile for the specific repair.

Cleanup – It is important to remove excess adhesive from the work area and application equipment before it hardens. Denatured alcohol and many common industrial solvents are suitable for removing uncured adhesive. Consult your supplier's information pertaining to the safe and proper use of solvents.

Product form – This product is available in 1.5 pound (680 grams) pint kits and 6 ounce (100 grams) cartridges.

Bond Strength Performance

Dogbone Tension Strength

Dogbone tension strength tested per ASTM D638, type 1 after 24 hours cure at 77°F/25°C and 2 hours post cure at 160°F/71°C.

Test Temperature	Typical Results	
°F/°C	psi	MPa
77/25	1,650	11.4
160/71	525	3.6

Dogbone tension strength after environmental soaks at 77°F/25°C for 7 days:

Skydrol hydraulic fluid	1,650	11.4
Synthetic lubrication oil	1,650	11.4

Typical QC acceptance tests are cured density, dogbone tension at 77°F/25°C and Shore D Hardness.

Bulk Resin Properties

Shore D Hardness Tested per ASTM D2240

Test Temperature, °F/°C	Typical Results
77/25	65

General Instructions for Use

1. Hand sand area to be prepared to rough up the surface and to remove fluid/dirt contamination. Wipe with solvent after sanding to remove dust.
2. Mix entire components of either the pint or 6.0 oz cartridge kit. Do not partially weigh out adhesive as potential separation of the components can adversely affect properties.
3. Thoroughly mix the adhesive until color and consistency is homogeneous, typically 4 to 5 minutes.
4. Apply adhesive to sanded area and smooth with trowel. To aid in adhesion and minimize slump, apply a nylon vacuum bag over the adhesive and work in thoroughly with a trowel. Leave the vacuum bag on until material is cured and then remove.

5. Allow to set for 3 hours at 77°F/25°C before sanding. Temperature below 77°F/25°C will require longer set times for full cure. As a general rule, each 18°F/10°C below 77°F/25°C will require twice the cure time.
6. Lightly sand front and rear edges of repair to improve air flow.

Handling Precautions

Do not handle or use until the Material Safety Data Sheet has been read and understood.
For industrial use only.

General:

As with most epoxy based systems use the product with adequate ventilation. Do not get in eyes or on skin. Avoid breathing the vapors. Wash thoroughly with soap and water after handling. Empty containers retain product residue and vapors so obey all precautions when handling empty containers.

PART A

CAUTION! This material may cause eye and skin irritation or allergic dermatitis. It contains epoxy resins.

PART B

WARNING! This material causes eye and skin irritation or allergic dermatitis. It contains amines.

Hysol® is a registered trademark of Henkel Corporation.

Rev. 1/01

DISCLAIMER: The information supplied in this document is for guidance only and should not be construed as a warranty. All implied warranties are expressly disclaimed, including without limitation any warranty of merchantability and fitness for use. All users of the materials are responsible for assuring that it is suitable for their needs, environmental and use. All data is subject to change as Henkel deems appropriate.

Users should review the Materials Safety Data Sheet (MSDS) and product label for the material to determine possible health hazards, appropriate engineering controls and precautions to be observed in using the material. Copies of the MSDS and label are available upon request.



Henkel Corporation
Aerospace Group
2850 Willow Pass Road
P.O. Box 312
Bay Point, CA 94565 USA
925.458.8000
www.aerospace.henkel.com